

CANDESCENCE® Blister

VISUAL PACKAGING WITHOUT COMPROMISE

A more sustainable option than rigid plastic packaging. Our proprietary fiber and coating technology ensures consistent sealing, gluing, and adhesion with an ultra-smooth clay coated print surface for the most demanding blister applications.

PRODUCT USES

- Visual packaging
- Health and beauty packaging
- Personal care products
- Office products
- Computer cables and accessory packaging
- Personal electronics packaging



CANDESCENCE® BLISTER TYPICAL VALUES

English	Units	12-143	14-163	16-182	18-199	20-217	24-250	26-273
Caliper (nominal)	mils	12	14	16	18	20	24	26
Basis Weight (nominal)	lbs/3msf	143	163	182	199	217	250	273
Brightness	GE	89	89	89	89	89	89	89
b*Value	Spectro	1.2	1.2	1.2	1.2	1.2	1.2	1.2
Smoothness (primary side)	Sheffield	17	18	19	23	27	30	32
Parker Print (primary side)	microns	1.2	1.2	1.2	1.2	1.2	1.2	1.2
Plybond	lbs/in2	47	42	37	35.5	35.5	35.5	35.5
Stiffness – MD	Taber g-cm	90	125	160	215	265	415	495
Stiffness – CD	Taber g-cm	52	68	90	125	150	225	270
Metric	Units	305-233	356-265	406-296	457-324	508-353	610-407	660-444
Thickness	microns	305	356	406	457	508	610	660
Basis Weight	g/sq.m	233	265	296	324	353	407	444
Stiffness – MD	mN	176	245	314	421	519	813	970
Stiffness – CD	mN	102	133	176	245	294	441	529