ANCORA® C2S

TWO-SIDED DEPENDABILITY

The premier choice for side-to-side consistency. The ultra-smooth print surface and fiber strength will consistently hold up to your most demanding print applications such as varnishing treatments, foil stamping and embossing.

PRODUCT USES

- Presentation folders
- Luxury merchandise packaging
- Point of purchase displays
- Digital printing
- Brochures
- Direct mailers

ANCORA® C2S TYPICAL VALUES

English	Units	10-144	12-167	14-188	16-203	18-220	20-240	22-265	24-286
Caliper (nominal)	mils	10.0	12.0	14.0	16.0	18.0	20.0	22.0	24.0
Basis Weight (nominal)	lbs/3msf	144	167	188	203	220	240	265	286
Brightness (both sides)	GE	89	89	89	89	89	89	89	89
b* Value (both sides)	Spectro	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Smoothness (both sides)	Sheffield	12	15	18	18	20	20	22	25
Parker Print (both sides)	microns	1.1	1.1	1.2	1.2	1.3	1.3	1.3	1.3
Plybond	lbs/in2	56	52	48	48	45	45	45	45
Stiffness – MD	g-cm	50	80	120	170	230	300	400	470
Stiffness – CD	g-cm	25	40	60	85	115	155	205	250
Metric	**Units**	**254-234**	**305-272**	**356-306**	**406-330**	**457-358**	**508-391**	**559-431**	**610-465**
Thickness	microns	254	305	356	406	457	508	559	610
Basis Weight (nominal)	gsm	234	272	306	330	358	391	431	465
Stiffness – MD	mN	102	162	244	345	467	609	812	954
Stiffness – CD	mN	51	81	122	173	233	315	416	508